

Boat and Tooling Fabrics

Fabric Style	Standard	Weave	Weight oz./sq. yd.	Thickness (inch)	Count Warp X Fill	Yarn Warp	Yarn Fill	Breaking Strength (lbs. / inch of width)		Roll Length (Yards)
	Width (Inches)							Warp	Fill	
1522	50"	Plain	3.82	.0056	24 X 22	ECG 150 1/2	ECG 150 1/2	140	140	125
1522	60"									125
7533	38"	Plain	5.85	.0080	18 X 18	ECG 75 1/2	ECG 75 1/2	220	220	125
7533	50"									125
7533	60"									125
7532	38"									Plain
7532	44"	125								
7532	50"	125								
7532	60"	125								
7520	38"	Plain	8.68	.0120	18 X 18	ECG 75 1/3	ECG 75 1/3	330	330	125
7520	50"									125
7500	38"	Plain	9.60	.0110	16 X 14	ECG 75 2/2	ECG 75 2/2	300	250	125
7500	44"									125
7500	50"									125
7500	60"									125
2532	38"	Plain	7.23	.0100	16 X 14	ECH 75 1/3	ECH 75 1/3	250	200	125
2532	50"									125
2532	60"									125
4700	38"	Plain	4.35	.0077	14 X 13	ECG 37 1/0	ECG 75 1/0	250	165	125
3733	38"	Plain	5.80	.0080	18 X 18	ECG 37 1/0	ECG 37 1/0	250	200	150
3733	50"									150
3733	60"									150
1800	38"	Plain	9.80	.0120	16 X 14	ECK 18 1/0	ECK 18 1/0	450	300	150
1800	50"									150
1800	60"									150
7544	38"	Plain	18.0	.020	28 X 14	ECG 75 2/2	ECG 75 2/4	500	500	100
7544	44"									100
7544	50"									100
7587	38"	Mock Leno	20.5	.0300	42 X 21	ECG 75 2/2	ECG 75 2/2	750	450	100
7597	38"	Dbl. Satin	39.2	.0450	30 X 30	ECG 75 2/4	ECG 75 2/4	1463	1463	50